




## Typical Particle Size Analysis and Properties 8/16 Industrial Sand

| US Standard Sieve | Individual % Retained |
|-------------------|-----------------------|
| 6                 | 0.0                   |
| 8                 | 4.0                   |
| 10                | 10.3                  |
| 12                | 17.2                  |
| 14                | 31.5                  |
| 16                | 26.7                  |
| 18                | 8.6                   |
| 20                | 0.9                   |
| 25                | 0.4                   |
| 30                | 0.3                   |
| 35                | 0.1                   |
| 40                | 0.0                   |
| Pan               | 0.0                   |

These do not represent a specification

**Plant Office**  
651 Keuka Road  
Edgar, FL 32640



SINCE 1892

**Corporate Office**  
Post Office Box 3033  
Davenport, FL 33836