



Typical Particle Size Analysis and Properties

Commercial Concrete Sand

US Standard Sieve	% Passing
4	99.1
8	95.9
16	87.2
30	72.5
50	35.2
100	0.7
Pan	0.0
Fineness Modulus	2.10
Effective Size	0.19
Uniformity Co-efficient	2.62

These do not represent a specification

Plant Office
651 Keuka Road
Edgar, FL 32149



SINCE 1892

Corporate Office
Post Office Box 3033
Davenport, FL 33836