




Typical Particle Size Analysis and Properties Edgar Glass Sand

US Standard Sieve	Cumulative % Retained
20	0.1
30	0.5
40	8.1
50	25.3
70	44.6
100	68.1
140	96.2
Pan	100.0

These do not represent a specification

Plant Office
651 Keuka Road
Edgar, FL 32640



SINCE 1892

Corporate Office
Post Office Box 3033
Davenport, FL 33836